



- TECHNICAL DATA SHEET -

SYNTHITE ER-41 RED INSULATOR 160°C (Red insulating protective enamel)

DESCRIPTION

SYNTHITE ER-41 Red Insulator (class F) is a protective high temperature insulating enamel that dries very quickly, forming a tough and flexible film with excellent heat and chemical resistance. It has the following outstanding properties:

- Very fast air drying.
- Excellent chemical resistance.
- Oil and moisture resistant.
- Hard, smooth, abrasion resistant film.
- Excellent adhesion.

CHARACTERISTICS

Physical properties

Color	Red
Specific gravity at 25°C	950±50gr/lt
Viscosity in Ford Cup n. 4 at 25°C	90-120"
Viscosity in Demmler Cup n.1 at 30°C	70-100"
Build up, D.F.T. (ASTM D-115-55)	mm.0,075 / 0,100
Thinner	Dolph's T-200
Air Drying time (on a copper plate)	Set to touch: 60'
Corrosive effects on copper	None

Electrical Properties

Dielectric Strength (dry)	2000Volts/mm.0,025
Dielectric Strength (after 24h. dipping into water)	1200 Volts/mm.0,025

Chemical resistance

Water.	Excellent
Acid (10% Sulfuric Acid)	Excellent
Alkali (1% Sodium Hydroxide)	Excellent
Salt water	Excellent
Mineral Oil, ASTM D-115-55	Passed

APPLICATION

SYNTHITE ER-41 Red Insulator dries very quickly to a uniform, glossy finish that gives a superior abrasion resistance and an excellent adhesion to most surfaces.

It is suitable as a protective coating for stator coils, transformer coils, armature coils, bus bars, field coils, control coils, commutator ends, collector rings, oil reservoir interiors, switch bases, porcelain, molded bakelite, solenoid coils, motor frames and so on.

SYNTHITE ER-41 is supplied with a viscosity suitable for application by brush. For spraying application, it must be thinned with 15% about of Dolph's T-200 thinner.

SYNTHITE ER 41 is also available in spray cans.

Warning: All the information and application instructions concerning this product are based on technical specifications that we consider reliable, and are provided by way of example, according to our application experience. They do not establish any guarantee but only represent a starting point subject to alterations, according to the application and the kind of material to be treated. Before the product's use the user must determine the suitability for the intended use undertaking all risks and responsibility for whatever may happen in connection with the application. The producer and/or seller will not be considered responsible for any accident, loss or damage (immediate or consequent) originating from the use and/or the inability to use the concerned product. Albesiano Sisa Vernici srl reserves the right to change or modify at any time and without any notice the technical specifications of the product described in this data sheet.

File: ER-41 ing	Issued: 17.04.02	Updated: 10.06.04	Drawer: Massimiliano Balboni	This document cancels and replaces all previous ones
-----------------	------------------	-------------------	------------------------------	--